




PRODUCT INFORMATION



Product Name:	<u>MORDANT SOLUTION TYPE 'T'</u> <u>HIGHWAYS AGENCY ITEM NO.155</u>
Reference Number:	150-23
Use:	Pre-treatment for galvanised steel to improve adhesion of subsequent coating system.
Composition:	A blend of copper carbonate, phosphoric acid, water and alcohols complying with the B.R. Specification for 'T'-Wash. See BS5493 Table 4N Section E.
Theoretical Coverage:	20-25m ² per litre.
Drying Time at 20°C: (Will vary with temperature, air movement etc.)	Touch Dry: 20-60 minutes (depending on site/application conditions). Overcoat: As soon as surface is completely dry.
Packaging:	1 litre, 2.5 litre, 5 litre and 25 litre plastic containers.
Shelf Life:	12 months in unopened containers, when stored under cover in good storage conditions.
Storage:	Under cover within temperature range of 5°C to 32°C.
Surface Preparation:	Degrease galvanised surface with Dacrylate Thinner R5.
Application:	Apply by brush to clean degreased surface and allow to dry. Avoid excess application and "ponding" . After drying, excess 'T'-Wash should be wet-cleaned to remove surplus 'T'-Wash and allowed to dry. When dry, the galvanised surface should be "blackened". Any areas still showing a bright galvanised surface indicates presence of contamination. Lightly abrade these areas, degrease and re-apply Mordant Solution.
<u>Note:</u>	On weathered galvanising the appearance after treatment may vary from Black to Light Grey.
Clean Up:	Clean brushes in water.
Health and Safety:	Please see relevant MSDS sheet.

Data sheets are issued to supply **general information** on the product but without warranty. Since conditions of service and application are beyond our control we cannot accept claims for loss, damage etc., based on this information. Dacrylate will not accept any claim for consequential or incidental damages.

Issued: November 2001

SW/DAE/CR