



PRODUCT INFORMATION



Product Name:	VEHICLE AND MACHINERY ENAMEL
Reference Number:	97-Line.
Coating Type:	Modified alkyd.
Typical Uses:	Finishing coat for vehicles, plant and machinery. Excellent durability with good resistance to oils, grease, etc. Dries to hard film with hard abrasion and impact resistance.
Colours Available:	As industrial shade card. (All British Standard and RAL shades available on Dacmix tinting scheme.)
Appearance of Dried Film:	Gloss.
Volume Solids:	40% (may vary with colour).
Dry Film Thickness:	Typical: 40 microns. Range: 30-50 microns.
Theoretical Coverage:	10m ² per litre at 40 microns dry film thickness.
Drying Time at 20°C: (Will vary with temperature, air movement etc.)	Touch Dry: 1 hour. Firm Dry: 4 hours. Overcoat: Overnight or within 1 hour (see note overleaf).
Packaging:	5 litre containers.
Shelf Life:	2 years in unopened containers, when stored under cover in good storage conditions.
Storage:	Under cover within temperature range of 5°C to 32°C.

Continued/

Surface Preparation:	Normally applied over Dacrylate range of primers, e.g. 95-line, 98-line, etc. Ensure surface is clean and dry.
Application:	Brush: Supplied ready for use. Conventional or airless spray: May require addition of up to 15% Dacrylate Thinner R70 to achieve optimum spray characteristics.
Overcoating:	Should a second coat of Vehicle and Machinery Enamel be required, this can be applied as soon as the first coat is touch dry, i.e. up to 1 hour – <u>or</u> allow coating to dry overnight.
Clean Up:	Dacrylate Thinner R1 or R70.
Health and Safety:	Please see relevant MSDS sheet.

Data sheets are issued to supply **general information** on the product but without warranty. Since conditions of service and application are beyond our control we cannot accept claims for loss, damage etc., based on this information. Dacrylate will not accept any claim for consequential or incidental damages.